


Woodoc Deck Sealer Specification Sheet



Typical Application:

A tinted, low-gloss, exterior sealer for use on wooden decks made of porous (soft) wood e.g. SA Pine and porous Meranti. It was formulated specifically for use on porous wooden decks and all other exterior woodwork exposed to harsh weather.

Please note: Not suitable for use on Balau decks. Use Woodoc Deck Dressing on Balau decks as well as decks made of other dense wood types.

Product Features:

Woodoc Deck Sealer is alkyd-based with UV-absorbers and added transparent iron oxides to protect wood against harsh sunlight.

- Excellent wind, water, pollution and salt spray protection.
- Superior Ultra-violet radiation protection in extreme conditions.
- High-build characteristic for a smooth and attractive low-gloss surface.
- Available in Golden Brown, Rich Meranti and Deep Brown.
- Deep penetrates to nourish wood.
- Non-toxic when dry.
- Does not affect glue.
- Bio-degrades at the end of its life cycle.
- Complete how-to-use instructions on label.

No: WDS/002 Dated: **10/11/11**

Name: Woodoc Deck Sealer - Exterior Low-Gloss Sealer (Rich Meranti / Deep Brown / Golden Brown)

Description:

Deep penetrating, tinted, low-gloss finish with UV-protection and water repellence, for outdoor use.

Coverage:

First coat 10-12 m²/litre. Subsequent coats 12-14 m²/litre. 3 coats (average) 3,3 m²/litre.

Application:

By brush. Clean brush with mineral turpentine.

Dilution:

Dilution is not recommended, but should dilution be necessary, use only mineral turpentine.

Drying Time:

Drying will vary, depending on moisture and atmospheric conditions.

Product Properties:

Tinted, low-gloss, high-build, exterior wood sealer.

Wax Content:

None.

Compatibility:

Mineral Turpentine.

Non-Compatibility:

Acetone, Lacquer Thinners, Benzene, and other solvents.

Packaging:

1 litre and 5 litres. (20 or 200 litres available on request from dealer)

ALWAYS READ THE DIRECTIONS ON THE TIN BEFORE STARTING WORK.

FLAMMABLE. Keep out of reach of children. Harmful when consumed. Ingestion may cause chemical pneumonitis.

IMPORTANT: This product hardens through contact with air (oxygen). Replace lid firmly after use to prolong pot life.



Manufactured and marketed by:
Rekara Mills (Pty) Ltd
PO Box 16, Fort Beaufort 5720, South Africa
Tel +2746 645 1109 Fax +2746 645 1538

Customer Service:

Toll-Free during office hours 0800 411 200 (South Africa only)

Email: information@woodoc.com or visit www.woodoc.com