

Woodoc 30 Specification Sheet



Typical Application:

Woodoc 30 is a clear, low-gloss, exterior sealer that enhances the natural look and colour of wood. Ideal for doors, window frames, garage doors and wooden garden furniture.

Product Features:

Woodoc 30 is moisture repellent, has a wax fraction that feeds the wood and combats fungus growth, and a UV absorber that protects the wood against the sun's rays.

- Protects exterior wood against seasonal and environmental moisture variation.
- Offers excellent protection against ultra-violet radiation.
- Enhances the grain and natural colour of the wood.
- Deep penetrates to nourish wood and combats fungus growth.

Biodegrades at the end of its life cycle. No need for scraping or sanding. Clean the old surface with Woodoc SteelWool and mineral turpentine before re-applying Woodoc 30.

No: WD30/002

Dated: 01/10/04 **Replacing:** New

Name:

Woodoc 30 - Exterior Polywax Sealer (Clear)

Description:

Deep penetrating, clear, low-gloss finish with UV protection and water repellence, for outdoor use.

Coverage:

First coat 10-12m²/litre. Subsequent coats 12-14m²/litre. 3 coats (average) 3,3m²/litre.

Application:

By brush. Clean brush with mineral turpentine.

Dilution:

Dilution is not recommended, but should dilution be necessary, use only mineral turpentine.

Drying Time:

Sand: 6 - 12 hours.

Hard: 12 - 24 hours.

Drying will vary, depending on moisture and atmospheric conditions.

Product Properties:

Clear, low-gloss, exterior wood sealer with preservative and anti-fungal properties.

Wax Content:

Low.

Compatibility:

Mineral Turpentine.

Non-Compatibility:

Acetone, Lacquer Thinners, Benzene and other solvents.

Packaging:

500 ml, 1 litre and 5 litres.

ALWAYS READ THE DIRECTIONS ON THE TIN BEFORE STARTING WORK.

FLAMMABLE. Keep out of the reach of children. Harmful when consumed. Ingestion may cause chemical pneumonitis.

IMPORTANT: This product hardens through contact with air (oxygen). Replace lid firmly after use to prolong pot life.



Manufactured and marketed by:

Rekara Mills (Pty) Ltd

PO Box 16, Fort Beaufort 5720, South Africa

Tel +2746 645 1109 Fax +2746 645 1538

Customer Service:

Toll free during office hours 0800 411 200 (South Africa only)

Email: information@woodoc.com or visit www.woodoc.com