

Woodoc 35 Specification Sheet



Typical Application:

Woodoc 35 is a tinted, low gloss, exterior sealer with added ultra-violet protection, suitable for harder, darker woods. Woodoc 35 is available in Meranti, Dark Brown and Russet. Ideal for doors, window frames and garage doors exposed to intense sunlight.

Product Features:

Woodoc 35 contains transparent iron oxides, which provide extra protection against harsh sunlight. It is moisture repellent and combined with the deep penetrating action and wax fraction, combats fungus growth.

- Protects exterior wood against seasonal and environmental moisture variation.
- Superior ultra-violet radiation protection.
- Enhances the grain and colour of darker wood.
- Deep penetrates to nourish wood and combats fungus growth.

Biodegrades at the end of its life cycle. No need for scraping or sanding. Clean the old surface with Woodoc SteelWool and mineral turpentine before re-applying Woodoc 35.

No: WD35/002

Dated: 01/10/04 **Replacing:** New

Name:

Woodoc 35 - Exterior Polywax Sealer (Meranti / Dark Brown / Russet)

Description:

Deep penetrating, tinted, low-gloss finish with extra UV protection and water repellence, for outdoor use.

Coverage:

First coat 10-12m²/litre. Subsequent coats 12-14m²/litre. 3 coats (average) 3,3m²/litre.

Application:

By brush. Clean brush with mineral turpentine.

Dilution:

Dilution is not recommended, but should dilution be necessary, use only mineral turpentine.

Drying Time:

Sand: 6 - 12 hours.

Hard: 12 - 24 hours.

Drying will vary, depending on moisture and atmospheric conditions.

Product Properties:

Tinted, low gloss, exterior wood sealer with preservative and anti-fungal properties.

Wax Content:

Low.

Compatibility:

Mineral Turpentine.

Non-Compatibility:

Acetone, Lacquer Thinners, Benzene and other solvents.

Packaging:

500 ml, 1 litre and 5 litres.

ALWAYS READ THE DIRECTIONS ON THE TIN BEFORE STARTING WORK.

FLAMMABLE. Keep out of the reach of children. Harmful when consumed. Ingestion may cause chemical pneumonitis.

IMPORTANT: This product hardens through contact with air (oxygen). Replace lid firmly after use to prolong pot life.



Manufactured and marketed by:

Rekara Mills (Pty) Ltd

PO Box 16, Fort Beaufort 5720, South Africa

Tel +2746 645 1109 Fax +2746 645 1538

Customer Service:

Toll free during office hours 0800 411 200 (South Africa only)

Email: information@woodoc.com or visit www.woodoc.com