

Woodoc 50 Specification Sheet



Typical Application:

For exterior use where a clear, gloss sealer providing a high build-up of product is required. Provides UV-protection and is water repellent. Ideal for yachts, boats, gates, garage doors and window frames. **Not suitable for use on hard, dense wooden decks.**

Product Features:

Woodoc 50 is a clear exterior gloss sealer that enhances the natural appearance and colour of wood. The product provides excellent protection against ultra-violet radiation, wind, water, pollution and salt spray damage.

- Contains a special alkyd base that remains flexible preventing surface cracking associated with temperature variation.
- Ultra-violet radiation protection in extreme conditions.
- Suitable for all wood types.
- High-build characteristic for a smooth gloss surface.
- Deep penetrates to nourish wood.
- Non-toxic when dry.
- Does not affect glue.
- Biodegrades at the end of its life cycle.
- Complete how-to-use instructions on label.

No: WD50/003

Dated: 02/11/11

Name:

Woodoc 50 - Exterior Gloss Sealer (Clear) (Marine)

Description:

Deep penetrating, clear, gloss finish with UV-protection and water repellence, for outdoor use.

Coverage:

First coat 10-12 m²/litre. Subsequent coats 12-14 m²/litre. 3 coats (average) 3,3 m²/litre.

Application:

By brush. Clean brush with mineral turpentine.

Dilution:

Dilution is not recommended, but should dilution be necessary, use only mineral turpentine.

Drying Time:

Drying will vary, depending on moisture and atmospheric conditions.

Product Properties:

Clear, gloss, high-build, exterior wood sealer. Formaldehyde-Free.

Wax Content:

None.

Compatibility:

Mineral Turpentine.

Non-Compatibility:

Acetone, Lacquer Thinners, Benzene and other solvents.

Packaging:

500 ml, 1 litre and 5 litres. (20 or 200 litres available on request from dealer)

ALWAYS READ THE DIRECTIONS ON THE TIN BEFORE STARTING WORK.

FLAMMABLE. Keep out of reach of children. Harmful when consumed. Ingestion may cause chemical pneumonitis.

IMPORTANT: This product hardens through contact with air (oxygen). Replace lid firmly after use to prolong pot life.



Manufactured and marketed by:

Rekara Mills (Pty) Ltd

PO Box 16, Fort Beaufort 5720, South Africa

Tel +2746 645 1109 Fax +2746 645 1538

Customer Service:

Toll free during office hours 0800 411 200 (South Africa only)

Email: information@woodoc.com or visit www.woodoc.com