

# Woodoc 50 Specification Sheet



## Typical Application:

Woodoc 50 is a clear, gloss, exterior marine sealer used extensively where a high build-up of sealer is required. Ideal for yachts, boats, gates, garage doors and window frames.

## Product Features:

Woodoc 50 gives excellent protection against ultra-violet radiation, wind, water, pollution and salt spray damage.

- Incorporates a special alkyd base that remains flexible preventing surface cracking associated with temperature variation.
- Ultra-violet radiation protection in extreme conditions.
- High build characteristic for a smooth gloss surface.
- Deep penetrates to nourish wood and combats fungus growth.

Biodegrades at the end of its life cycle. No need for scraping or sanding. Clean the old surface with Woodoc SteelWool and mineral turpentine before re-applying Woodoc 50.

**No:** WD50/002

**Dated:** 01/10/04 **Replacing:** New

## Name:

Woodoc 50 - Exterior Gloss Sealer (Clear) (Marine)

## Description:

Deep penetrating, clear, gloss finish with UV protection and water repellence, for outdoor use.

## Coverage:

First coat 10-12m<sup>2</sup>/litre. Subsequent coats 12-14m<sup>2</sup>/litre. 3 coats (average) 3,3m<sup>2</sup>/litre.

## Application:

By brush. Clean brush with mineral turpentine.

## Dilution:

Dilution is not recommended, but should dilution be necessary, use only mineral turpentine.

## Drying Time:

**Sand:** 6 - 12 hours.

**Hard:** 12 - 24 hours.

Drying will vary, depending on moisture and atmospheric conditions.

## Product Properties:

Clear, gloss, high build, exterior wood sealer with preservative and anti-fungal properties.

## Wax Content:

None.

## Compatibility:

Mineral Turpentine.

## Non-Compatibility:

Acetone, Lacquer Thinners, Benzene and other solvents.

## Packaging:

500 ml, 1 litre and 5 litres.

**ALWAYS READ THE DIRECTIONS ON THE TIN BEFORE STARTING WORK.**

**FLAMMABLE. Keep out of the reach of children. Harmful when consumed. Ingestion may cause chemical pneumonitis.**

**IMPORTANT: This product hardens through contact with air (oxygen). Replace lid firmly after use to prolong pot life.**



Manufactured and marketed by:

Rekara Mills (Pty) Ltd

PO Box 16, Fort Beaufort 5720, South Africa

Tel +2746 645 1109 Fax +2746 645 1538

Customer Service:

Toll free during office hours 0800 411 200 (South Africa only)

Email: [information@woodoc.com](mailto:information@woodoc.com) or visit [www.woodoc.com](http://www.woodoc.com)